

37
CLAIMS

WE CLAIM:



A combination of a laminate (400) and a substrate (450, 650) comprising:

a substrate (450, 650); and

a laminate (400) joined to said substrate (450, 650) at a seam (500), the laminate (400)

having a first layer (5) comprising a waterproof functional layer (10, 20), and a second layer (30) laminated to said first layer (5) and comprising at least a first component and a second component, the first component being stable to a first temperature and the second component melting at a second temperature, wherein the first temperature is higher than the second temperature.

2. The combination of claim 1, whereby the seam (500) withstands a water entry pressure of at least 0.07 bar.
3. The combination of claim 1, whereby the seam (500) withstands a water entry pressure of at least 0.13 bar.
4. The combination of claim 1, whereby the stiffness of the seam (500) is less than 50 mm^{-1} .
5. The combination of claim 1, whereby the shrinkage of the seam (500) is less than 7%.
6. The combination of claim 1, whereby the seam (500) has a width less than 0.25 cm.
7. The combination of claim 1, whereby the seam (500) has an elongation strain at break of greater than 75%.

8. The combination of claim 1, whereby the seam (500) has a transverse seam strength of greater than 3 pli.
9. The combination of claim 1, whereby the second layer (30) further includes a propellant which is activatable by activation means.
10. The combination of claim 1, whereby the second component is meltable at a temperature in the range from 80°C to 170°C.
11. The combination of claim 1, whereby the first component is stable to a temperature of at least 140°C.
12. The combination of claim 1, whereby the difference in temperature between the first temperature and the second temperature is at least 20°C.
13. The combination of claim 1, wherein the second layer (30) is composed of a plurality of yarns in the form of strands, filaments, threads or fibers.
14. The combination of claim 1, wherein the second layer (30) is a knitted, woven or non-woven layer.
15. The combination of claim 1, wherein the first component is selected from the group of polymers comprising polyolefins including polypropylene and polyethylene, polyester, co-polyester, polyamide, co-polyamide, cellulose or protein fibers including wool and silk.
16. The combination of claim 15, wherein the first component is polyamide 6.6.
17. The combination of claim 1, wherein the second component is a thermoplastic.

MISSING AT THE TIME OF PUBLICATION

MISSING AT THE TIME OF PUBLICATION

18 29.

The combination of claim 9, wherein the propellant is selected from the group of propellants consisting of azodicarbonamide, ammonium hydrogen carbonate, toluolsulfohydrazin or diazoaminobenzol.

~~1930.~~

18
m 29, v

The combination of claim ~~29~~, wherein the propellant is azodicarbonamide.

2031.

The combination of claim 1, wherein the functional layer (5) is a membrane or a film.

32.

10
n 31, v

The combination of claim 31, wherein the functional layer (5) is selected from the group of materials consisting of polyesters, polyamide, polyolefins, polyvinylchloride, polyketones, polysulfones, polycarbonates, fluoropolymers including polytetrafluoroethylene (PTFE), polyacrylates, polyurethanes, co-polyetheresters, co-polyetheramides.

22
33.

21
m 32, v

The combination of claim ~~21~~ 32, wherein the functional layer (5) is made from expanded PTFE.

23
34

The combination of claim 1, wherein the MVTR of the laminate (400) is less than 150 RET.

24
35

The combination of claim 1, wherein the water entry pressure of a laminate (400) is greater than 0.13 bar.

36.

Articles of clothing made from the combination of claims 1 to 35. ²⁴

37.

A combination of two laminates (400, 450, 650) joined together at a seam (500), each of the laminate (400, 450, 460) comprises:

a first layer (5) comprising a waterproof functional layer (10, 20), and

a second layer (30) laminated to said first layer (5) and comprising at least a first component and a second component, the first component being stable to a first temperature and the second component melting at

41

a second temperature, wherein the first temperature is higher than the second temperature.

27
38.

The combination of claim 37, whereby the seam (500) withstands a water entry pressure of at least 0.07 bar.

28
39.

The combination of claim 37, whereby the seam (500) withstands a water entry pressure of at least 0.13 bar.

29
40.

The combination of claim 37, whereby the seam (500) has a width less than 0.25 cm.

30
41.

The combination of claim 37, whereby the seam (500) has an elongation strain at break of greater than 75%.

31
42.

The combination of claim 37, whereby the seam (500) has a transverse seam strength of greater than 3 pli.

32
43.

The combination of claim 37, whereby the stiffness of the seam (500) is less than 50 mm⁻¹.

33
44.

The combination of claim 37, whereby the shrinkage of the seam (500) is less than 7%.

34
45.

The combination of claim 37, whereby the second layer further includes a propellant which is activatable by activation means.

35
46.

The combination of claim 37, whereby the second component is meltable at a temperature in the range from 80°C to 170°C.

36
47.

The combination of claim 37, whereby the first component is stable to a temperature of at least 140°C.

37
48.

The combination of claim 37, whereby the difference in temperature

26/26

1 2 3 4 5 6 7 8 9 10 11 12 13 14 15 16 17 18 19 20 21 22 23 24 25 26 27 28 29 30 31 32 33 34 35 36 37 38 39 40 41 42 43 44 45 46 47 48

between the first temperature and the second temperature is at least 20°C.

38
~~49~~

26
The combination of claim ~~37~~, wherein the second layer (30) is composed of a plurality of yarns in the form of strands, filaments, threads or fibers.

38
~~50~~

26
The combination of claim ~~37~~, wherein the first component is selected from the group of polymers comprising cellulose, protein fibers including wool and silk, polyolefins including polypropylene and polyethylene, polyester, co-polyester, polyamide, or co-polyamide.

40
~~51~~

39
The combination of claim ~~50~~, wherein the first component is polyamide 6.6.

41
~~52~~

26
The combination of claim ~~37~~, wherein the second component is a thermoplastic.

42
~~53~~

41
The combination of claim ~~52~~, wherein the second component is selected from the group of thermoplastics comprising co-polyester, polyamide, co-polyamide or polyolefin including polyethylene and polypropylene.

43
~~54~~

42
The combination of claim ~~53~~, wherein the second component is a polyethylene.

44
~~55~~

42
The combination of claim ~~54~~, wherein the second component is a polyamide 6.0.

45
~~56~~

38
The combination of claim ~~49~~, wherein the yarn has a bicomponent structure comprising the first component and the second component.

46
~~57~~

45
The combination of claim ~~56~~, wherein the yarn has a sheath-core structure, wherein the second component forms the cover.

47
~~58~~

45
The combination of claim ~~56~~, wherein the yarn has a "side-by-side"

26/26

49 50 51 52 53 54 55 56 57 58

structure.

~~48~~
59.

~~26~~
The combination of claim 37, wherein the second component is a blend of yarns.

~~49~~
60.

~~48~~
The combination of claim 59, wherein the yarn is comprised of fibers.

~~50~~
61.

~~31~~
The combination of claim 45, wherein the propellant after activation generates a closed cell foam with the second component after melting.

~~51~~
62.

~~31~~
The combination of claim 45, wherein the propellant is activated at a third temperature, the third temperature being intermediate between the second temperature and the first temperature.

~~52~~
63.

~~31~~
The combination of claim 45, wherein the propellant is an integral part of the second component.

~~53~~
64.

~~31~~
The combination of claim 45, wherein the propellant is selected from the group of propellants consisting of azodicarbonamide, ammonium hydrogen carbonate, toluolsulfohydrazin or diazoaminobenzol.

~~54~~
65.

~~53~~
The combination of claim 64, wherein the propellant is azodicarbonamide.

~~55~~
66.

~~29~~
The combination of claim 37, wherein the functional layer (5) is a membrane or a film.

~~56~~
67.

~~55~~
The combination of claim 66, wherein the functional layer (5) is selected from the group of materials consisting of polyesters, polyamide, polyolefins, polyvinylchloride, polyketones, polysulfones, polycarbonates, fluoropolymers including polytetrafluoroethylene, polyacrylates, polyurethanes, co-polyetheresters, co-polyetheramides.

~~57~~
68.

~~32~~
The combination of claim 67, wherein the functional layer (5) is made

Rel 26

11 12 13 14 15 16 17 18 19 20 21 22 23 24 25 26 27 28 29 30 31 32 33 34 35 36 37 38 39 40 41 42 43 44 45 46 47 48 49 50 51 52 53 54 55 56 57 58 59 60 61 62 63 64 65 66 67 68 69 70 71 72 73 74 75 76 77 78 79 80 81 82 83 84 85 86 87 88 89 90 91 92 93 94 95 96 97 98 99 100

from expanded PTFE.

~~58~~
~~69.~~

~~2b~~
The combination of claim ~~37~~, wherein the MVTR of the laminate (1) is greater than $3000 \text{ m}^2 / 24 \text{ hr}$.

~~59~~
~~70.~~

~~2b~~
The combination of claim ~~37~~, wherein the water entry pressure of a laminate (1) is greater than 0.13 bar.

~~60~~
~~71.~~
~~61~~
~~72.~~

~~2b~~
The combination of one of claims ~~37~~ to 70, in a garment.

A combination of two waterproof laminates (400, 450, 650), each having a functional layer (10, 20) laminated to a textile layer (30), and being joined together at a welded seam (500), wherein the seam (500) has a transverse seam strength of greater than 3 pli and an elongation strain at break greater than 75%.

~~62~~
~~73.~~

~~61~~
The combination of claim ~~72~~, wherein the seam (500) has a width of less than 0.25 cm.

~~63~~
~~74.~~

~~61~~
The combination of claim ~~72~~, wherein the stiffness of the seam (500) is less than 50 mm^{-1} .

~~64~~
~~75.~~

~~61~~
The combination of claim ~~72~~, wherein the seam (500) withstands water pressure of 0.13 bar for at least three minutes.

~~65~~
~~76.~~

~~61~~
The combination of claim ~~72~~, wherein the seam (500) shrinks by less than 7% after welding.

~~66~~
~~77.~~

A combination of two waterproof laminates (400, 450, 650), each having a functional layer (10, 20) laminated to a textile layer (30), and being joined together at a welded seam (500), wherein the seam (500) has a transverse seam strength of greater than 3 pli and wherein the stiffness of the seam (500) is less than 50 mm^{-1} .

~~67~~ 78

The combination of claim ~~45~~ 45, wherein the seam (500) has a width of less than 0.25 cm.

~~68~~ 79

The combination of claim ~~45~~ 45, wherein elongation strain at break is greater than 75%.

~~69~~ 80

The combination of claim ~~45~~ 45, wherein the seam (500) withstands a water pressure of 0.13 bar for at least three minutes

~~70~~ 81

Method for sealing a pinhole (800) in a laminate (810) having a waterproof and breathable functional layer (10, 20) laminated to a textile layer (30) comprising the following steps:

-detection of the pinhole (800).

-heating the laminate (810) to a temperature within the melting range of one or more of the components of the laminate (810) such that the one or more component flows and seals said pinhole (800).

~~71~~ 82

Method according to claim ~~81~~ 81, wherein said textile layer (30) is made of a plurality of conjugate yarns.

~~72~~ 83

Method according to claim ~~81~~ 81, wherein said textile layer (30) is heated to a temperature within the melting range of one or more of the components of the textile layer (30) such that the one or more of the components of the textile layer (30) flows and seals said pinhole (800).

Rh/26

[Signature]